

Automotive Foam



| Product code | Density | color | Hardness 50% [N] | Resilience | Applicable Standard | Application |
|--------------|---------|--------|------------------|------------|--|--|
| 018GYLG | 18+/-1 | Grey | 140+/-20 | 35% min | IS7888, ASTM-3574 | Automobiles Seat Covers with vinyl lamination Seat Covers with Textile Fabric lamination Car Door Trims Car upholstery |
| 018GYFR | 18+/-1 | Grey | 105+/-15 | 35% min | IS7888, FMVSS-302 | |
| 023GYFR | 23+/-1 | Grey | 140+/-20 | 35% min | IS7888, FMVSS302, Cal-117,UL-94 | |
| 026GYFR | 26+/-1 | Grey | 130+/-30 | 35% min | IS7888, FMVSS302, Cal-117,UL-94 | |
| 026GYRG | 26+/-1 | Grey | 230+/-30 | 35% min | IS7888, ASTM-3574 | |
| 028GYFR | 28+/-2 | Grey | 160+/-30 | 35% min | IS7888, FMVSS302, Cal-117,UL-94 | Automobiles Door trims |
| 028WHBS | 28+/-2 | White | 170 +/-30 | 35% min | IS7888, FMVSS302, Cal-117,UL-94 BSS 5852 Crib5 | |
| 032GYFR | 32+/-2 | Grey | 240+/-30 | 35% min | IS7888, ASTM-3574 | |
| 035YECL | 35+/-2 | Yellow | >500 | 30% min | IS7888, FMVSS-302 | Automobiles Sun visors |
| 035YEHR | 35+/-2 | Yellow | >500 | 30% min | IS7888 | |
| 035GYHR | 35+/-2 | Grey | >500 | 30% min | IS7888 | |
| 035GYCL | 35+/-2 | Grey | >500 | 30% min | IS7888,FMVSS-302 | |
| | | | | | | |