

Rebonded Foam



Product code	Density Kg/m ³	Hardness 50% [N]	Resilience	Applicable Standard	Application
080RB	80+/-5	500+/-50	25% min	IS-7888, ASTM-3574	Economical Mattress bottom layer, (Coir replacement)Packaging
090RB	90+/-5	<500	25% min	IS-7888, ASTM-3574	Economical Mattress bottom layer , (Coir replacement) Breakable article Packing
100RB	100+/-5	<500	25% min	IS-7888, ASTM-3574	Equipment Vibration pads, Lager Sensitive Packing (stone statues, Glass, Granite, etc..)
120RB	120+/-7	<500	25% min	IS-7888, ASTM-3574	